

10/733,660

Amdt. Dated Oct. 05, 2005

Resp. to Off. Action dated Aug. 31, 2005

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Please cancel claims 1-19, 21-30 and 32-36.

Listing of Claims:

1-19 (Canceled).

20. (CURRENTLY AMENDED) A golf ball comprising:

a core, the core having a diameter ranging from 1.2 inches to 1.6 inches ~~1.62 inches~~, a mass ranging from 25 to 40 grams, a PGA compression 70 or less, and a coefficient of restitution greater than 0.750 at an incoming speed of 125 feet per second;

an inner cover layer which has a Shore D hardness of at least 60 as measured on the curved surface thereof and is formed from a composition which includes at least one material selected from the group consisting of polyamides, polyester elastomers, polyester amides, metallocene catalyzed polyolefins, and blends thereof, the inner cover layer having a thickness ranging from 0.03 inch to 0.07 inch ~~0.003 to 0.007 inch~~; and

an outer cover layer formed over the inner cover layer, the outer cover layer having a Shore D hardness of no more than 55 as measured on the curved surface thereof; wherein the golf ball has a spin factor of at least 5.

21-30 (Canceled).

10/733,660

Amdt. Dated Oct. 05, 2005

Resp. to Off. Action dated Aug. 31, 2005

31. (CURRENTLY AMENDED) A golf ball comprising:

a solid core, the solid core having a diameter ranging from 1.2 inches to 1.6 ±.62 inches, a mass ranging from 25 to 40 grams, a PGA compression 70 or less, and a coefficient of restitution greater than 0.750 at an incoming speed of 125 feet per second;

an inner cover layer which has a Shore D hardness of at least 60 as measured on the curved surface thereof and is formed from a composition which includes at least one material selected from the group consisting of polyamides, polyester elastomers, polyester amides, metallocene catalyzed polyolefins, and blends thereof, wherein the inner cover layer has a thickness ranging from 0.03 inch to 0.07 inch ~~0.003 to 0.007 inch~~; and

an outer cover layer formed over the inner cover layer, the outer cover layer having a Shore D hardness of no more than 55 as measured on the curved surface thereof, wherein the outer cover layer has a thickness of from about 0.01 to about 0.10 inches;

wherein the golf ball has a spin factor of at least 8.

32-36 (Canceled).